

5/5/1

DIALOG(R) File 351:Derwent WPI

(c) 2002 Derwent Info Ltd. All rts. reserv.

012350296 **Image available**

WPI Acc No: 1999-156403/199914

XRAM Acc No: C99-046238

XRPX Acc No: N99-113068

Supertwist nematic liquid crystal

Patent Assignee: SHARP KK (SHAF)

Inventor: MOLSEN H; TILLIN M; TILLIN M D

Number of Countries: 027 Number of Patents: 004

Patent Family:

Patent No	Kind	Date	Applicat No	Kind	Date	Week
GB 2329481	A	19990324	GB 9719862	A	19970919	199914 B
EP 903392	A1	19990324	EP 98307529	A	19980916	199916
JP 11249118	A	19990917	JP 98265442	A	19980918	199949
KR 99029970	A	19990426	KR 9838864	A	19980919	200028

Priority Applications (No Type Date): GB 9719862 A 19970919

Patent Details:

Patent No	Kind	Lan	Pg	Main IPC	Filing Notes
GB 2329481	A		23	G02F-001/139	
EP 903392	A1	E		C09K-019/54	

Designated States (Regional): AL AT BE CH CY DE DK ES FI FR GB GR IE IT

LI LT LU LV MC MK NL PT RO SE SI

JP 11249118 A 8 G02F-001/1333

KR 99029970 A G02F-001/133

Abstract (Basic): GB 2329481 A

NOVELTY - A supertwist nematic liquid crystal has two substrates defining a cell between them which contains a nematic LC and a helical polymer network.

DETAILED DESCRIPTION - In an INDEPENDENT CLAIM, a supertwisted LCD is formed by filling a cell formed between two substrates with a nematic LC and a chiral prepolymer and polymerizing or crosslinking the prepolymer to form a polymer network (19).

USE - For manufacturing supertwisted nematic (STN) LCD.

ADVANTAGE - The use of the networked polymer gives a more stable polymer orientation and avoids hysteresis in the electrooptic curve. The use of low pre-tilt alignment layers reduces device switching times so that the required time to switch between two states of a typical device are in the order of 40 milliseconds.

DESCRIPTION OF DRAWING(S) - The drawing shows a cross-sectional view of the device after polymerisation or crosslinking to form a STNLCD.

Polarisers (10, 11)

substrates (12,13)

Alignment layers (16, 17)

LC+ polymer network (19)

pp; 23 DwgNo 4/7


Title Terms: NEMATIC; LIQUID; CRYSTAL

Derwent Class: A35; A85; L03; P81; U14

International Patent Class (Main): C09K-019/54; G02F-001/133; G02F-001/1333; G02F-001/139

International Patent Class (Additional): C09K-019/02

File Segment: CPI; EPI; EngPI



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 0 903 392 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
24.03.1999 Bulletin 1999/12

(51) Int Cl.⁶: **C09K 19/54, C09K 19/02**

(21) Application number: **98307529.2**

(22) Date of filing: **16.09.1998**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**
Designated Extension States:
AL LT LV MK RO SI

(72) Inventors:
• **Molsen, Henning**
Oxford OX2 ODF (GB).
• **Tillin, Martin**
Abingdon, Oxfordshire OX14 2PG (GB)

(30) Priority: **19.09.1997 GB 9719862**


(71) Applicant: **Sharp Kabushiki Kaisha**
Osaka 545-8522 (JP)

(74) Representative: **Asquith, Julian Peter et al**
Marks & Clerk,
4220 Nash Court,
Oxford Business Park South
Oxford OX4 2RU (GB)

(54) **Supertwisted nematic liquid crystal device and method of making such a device**

(57) A supertwisted nematic liquid crystal device comprises substrates (12) and (13) carrying external polarisers (10) and (11), electrodes (14) and (15), and alignment layers (16) and (17). The resulting liquid crystal

cell is filled by a mixture (18) comprising a nematic liquid crystal and at least one chiral prepolymer having at least two polymerisable groups, such as a diacrylate. The prepolymer is polymerised or crosslinked to form a helical polymer network.



EP 0 903 392 A1

Description

[0001] The present invention relates to a supertwisted nematic liquid crystal device and to a method of making such a device.

[0002] Supertwisted nematic (STN) liquid crystal devices (LCDs) are known for use in displays and are disclosed, for instance, in C M Waters et al, "Mol Cryst Liq Cryst" Vol 123 pp 303 (1985). In such devices, a nematic liquid crystal is disposed in a cell and is arranged to have a twist angle typically of the order of 270 degrees. Design rules for STN displays are disclosed by Waters et al and the influence of various parameters, such as surface pre-tilt, twist angle and elastic constants, are explored.

[0003] In such STN devices, each picture element (pixel) is individually controllable so as to be switchable between a bright transmissive or reflective state and a dark transmissive or reflective state. Depending on the construction of the device, these two states correspond to the essentially planar orientation and the field-induced homeotropic orientation of the liquid crystal director.

[0004] The transition from the planar orientation to the homeotropic orientation is achieved by applying an electric field along the helical axis of the liquid crystal. This can result in either of two competing deformations of the helical pattern of the directors of the liquid crystal molecules. The first is the so-called Freedericksz transition in which the orientation of the local director changes only along a spatial co-ordinate substantially perpendicular to the liquid crystal layer. This is the desired transition. However, the second type of deformation results in a striped texture in which the local optic axis changes its orientation along two spatial co-ordinates, one of which is perpendicular to the liquid crystal layer and the other of which is parallel to the liquid crystal layer. This is disclosed by T Scheffer et al, "Twisted nematic and Supertwisted Nematic Mode LCDs" in "Liquid Crystals - Applications and Uses" Vol 1 pp 232 published by World Scientific Publishing Co Pte Ltd, Singapore 1990. For twist angles of up to about 300 degrees with typical liquid crystals, the stripes are oriented substantially perpendicularly to the local director in the middle of the liquid crystal layer. This transition results in optical hysteresis for relatively low magnitude applied fields, scattering and irreproducible transmission characteristics.

[0005] Figure 1 illustrates diagrammatically an STN-LCD having three sections or pixels operating in the field-induced homeotropic orientation at 1, in the planar orientation at 2, and with the striped texture at 3. In the field-induced homeotropic orientation, an electric field is applied across the liquid crystal layer of the pixel so that the liquid crystal molecule directors, indicated by short lines such as 4, are oriented throughout the bulk of the liquid crystal layer substantially perpendicularly to the layer. In the planar orientation illustrated at 2, the liquid crystal molecule directors 4 turn through an angle

of, for instance, substantially 270 degrees from one surface of the liquid crystal to the other surface thereof. This is the relaxed state of the liquid crystal with no applied electric field across the liquid crystal layer of the pixel.

[0006] In the striped texture illustrated at 3, the liquid crystal molecule directors 4 are twisted about an axis perpendicular to the liquid crystal layer, but are also rotated in planes containing that axis.

[0007] The graph above the liquid crystal device illustrated in Figure 1 indicates the light transmission for the liquid crystal cell disposed between linear polarisers having orthogonal polarisation directions. In the homeotropic texture illustrated at 1, the birefringence of the liquid crystal layer is such as to have little effect on the polarisation of light passing through the pixel. This is substantially equivalent to the effect of crossed polarisers so that the light transmissivity of the pixel is relatively low, as indicated by the curve at 5.

[0008] In the planar texture as illustrated at 2, the liquid crystal layer of the pixel has a birefringence such as to rotate the polarisation of light passing through the layer by 90 degrees. Accordingly, light leaving the pixel has a linear polarisation such that the output polariser provides relatively little attenuation and the pixel appears bright, as indicated by the curve at 6.

[0009] The striped texture illustrated at 3 provides a birefringence which varies periodically across the pixel. This leads to light and dark bands as illustrated by the undulating transmissivity curve at 7.

[0010] The striped texture is promoted by increasing twist angle and by reducing surface pre-tilt angles in the liquid crystal layer. For instance, Waters et al disclose that increasing the surface pre-tilt lowers the threshold voltage of the Freedericksz transition so as to avoid the formation of the striped texture. However, increasing the surface pre-tilt also increases the relaxation time of the transition from the homeotropic orientation to the planar orientation because the restoring surface forces become smaller as the surface pre-tilt increases. Accordingly, STNLCDS are designed as a compromise between the maximum refresh rate of the display and the likelihood of the occurrence of the striped texture.

[0011] D. Fredley et al, Journal of the SID Vol 4 pp 89 (1996) discloses a conventional STNLCDS in which a non-chiral non-mesogenic acrylate is cured by ultraviolet radiation while applying a high voltage across the liquid crystal cell to create a polymer network which is aligned substantially homeotropically in the cell. This technique is used to increase the tilt angle in the bulk of the liquid crystal layer, even in the "field-off" state. However, the need to apply a high voltage across the cell during manufacture is a considerable disadvantage because the increased complexity and cost.

[0012] H. Takatsu et al, SID95 Digest pp 579 (1995) disclose a guest-host liquid crystal device comprising a cell containing a mixture of nematic liquid crystal, a chiral monoacrylate prepolymer and a black dichroic mixture dye aligned on an alignment layer which gives a low

pre-tilt angle of the order of 1 degree. The prepolymer is cured by ultraviolet light which creates a helical side chain polymer. The ratio of the thickness of the liquid crystal cell to the pitch of the helical polymer is made greater than or equal to 1.25.

[0013] Such a device shows no focal conic texture and this is said to result from the vanishing twisting power of the fixed chiral polymeric dopend.

[0014] When a device of this type is used with a reflector on one side of the liquid crystal cell, a performance of the type illustrated in Figure 2 of the accompanying drawings is achieved. The graph of Figure 2 illustrates reflectance as a percentage against applied voltage for a typical cell of this type. As the voltage rises above a threshold of approximately 2.5 volts, the reflectance increases rapidly to a value above 30% and then rises more gently to a maximum reflectance slightly more than 40%. As the voltage is then decreased, the reflectance falls at first relatively slowly and then relatively rapidly to a relatively low or minimum value at 2 volts.

[0015] As is clear from Figure 2, the electrooptic performance of devices of this type possesses hysteresis. The presence of hysteresis is a substantial disadvantage because, when addressing a desired transmission state corresponding to a desired grey level, the addressing device is being switched from a brighter or darker state than the desired grey level. Conversely, if the same addressing voltage is used to address an intermediate grey level from brighter and darker states, the actual intermediate level achieved depends on whether the device is switched from a brighter or darker state. In order to avoid these problems with devices exhibiting hysteresis, it is necessary to ensure that, during each refresh cycle, the pixels are first reset to a common, generally dark, state before addressing the next desired state. However, this adds complexity and increases the time required to refresh the device.

[0016] According to a first aspect of the invention, there is provided a supertwisted nematic liquid crystal device comprising first and second substrates defining therebetween a cell containing a mixture of a nematic liquid crystal and a helical polymer network, wherein the polymer of the network comprises at least one polymerised chiral prepolymer. The nematic liquid crystal in the cell may have a twist angle of between substantially 180° and substantially 360°. The twist angle may be greater than 240°. The twist angle may be substantially equal to 270°.

[0017] The nematic liquid crystal in the cell may have a pre-tilt angle less than 4°. The pre-tilt angle may be substantially equal to 2°. The term "pre-tilt angle" is well known in the liquid crystal field and refers to the angle at which the liquid crystal director is tilted out of the substrate plane due to interaction with an alignment layer.

[0018] At least one of the first and second substrates may have an alignment layer for inducing planar alignment.

[0019] The polymer of the network may be a networked polymer. The term "networked polymer" as used herein refers to a polymer in a liquid crystal environment which is formed in a liquid crystal phase from mesogenic precursors having polymerisable moieties which can link to more than two other mesogenic precursors. The chiral prepolymer may comprise at least two polymerisable or crosslinkable groups. The prepolymer may comprise a diacrylate.

[0020] The polymer network may comprise at least 1% by weight of the mixture. The polymer network may comprise at least 1.5% by weight of the mixture.

[0021] The polymer network may comprise less than 20% by weight of the mixture. The polymer network may comprise less than 10% by weight of the mixture. The polymer network may comprise less than 5% by weight of the mixture.

[0022] The cell may be disposed between first and second polarisers. The first and second polarisers may have linear polarising directions oriented at between 0° and 90° with respect to each other.

[0023] The cell may be disposed between a polariser and a reflector.

An optical retarder may be disposed between the mixture and the polariser or between the mixture and the reflector.

[0024] According to a second aspect of the invention, there is provided a method of making a supertwisted nematic liquid crystal device, comprising juxtaposing first and second substrates to define there between a cell, filling the cell with a mixture comprising a nematic liquid crystal and a chiral prepolymer, and polymerising or crosslinking the prepolymer to form a polymer network.

[0025] The mixture may comprise a non-chiral prepolymer in addition to the chiral prepolymer.

[0026] The prepolymer may be a networkable prepolymer.

[0027] The chiral prepolymer may have at least two polymerisable or crosslinkable groups. The prepolymer may comprise a diacrylate.

[0028] The nematic liquid crystal in the cell may have a twist angle of between substantially 180° and substantially 360°. The twist angle may be greater than 240°. The twist angle may be substantially equal to 270°.

[0029] The nematic liquid crystal in the cell may have a pre-tilt angle less than 4°. The pre-tilt angle may be substantially equal to 2°.

[0030] The method may comprise forming on at least one of the first and second substrates, prior to the juxtaposition, an alignment layer for inducing planar alignment.

[0031] The prepolymer may comprise at least 1% by weight of the mixture. The prepolymer may comprise at least 1.5% by weight of the mixture.

[0032] The prepolymer may comprise less than 20% by weight of the mixture. The prepolymer may comprise less than 10% by weight of the mixture. The prepolymer

may comprise less than 5% by weight of the mixture.

[0033] The liquid crystal may have positive dielectric anisotropy and the polymerising or crosslinking may be performed in the absence of an applied field across the cell.

[0034] The liquid crystal may have negative dielectric anisotropy and, during polymerising or crosslinking, a field which provides planar alignment of the liquid crystal may be applied across the cell.

[0035] Locking the chirality in a polymer network prevents or substantially reduces the possibility of the formation of the striped texture. It is thus possible to produce a 270° STN device with an alignment layer inducing a pre-tilt 2° which can be commercially manufactured. Such a device is advantageous compared with known STN devices where the twist is limited to 240° with alignment layers inducing a relatively high pre-tilt, for instance greater than 4°. Further, it is possible to avoid the use of commercially unviable evaporated alignment layers, such as silicon oxide, which would otherwise be required in order to provide high pre-tilt alignment layers permitting a 270° twist.

[0036] The use of a networked polymer instead of a side chain polymer provides more stable polymer orientation and avoids hysteresis in the electrooptic curve. The use of low pre-tilt alignment layers reduces device switching times so that the required time to switch between the two states of a typical device may be of the order 40 milliseconds.

[0037] The invention will be further described, by way of example, with reference to the accompanying drawings in which:

Figure 1 is a diagrammatic cross sectional view with associated transmissivity curves of a known type of STN device;

Figure 2 is a graph of reflectance in per cent against applied voltage illustrating an electrooptic curve of a known type of twisted nematic liquid crystal device including a black dichroic dye mixture;

Figure 3 is a diagrammatic cross-sectional view of an STN device prior to polymerisation or crosslinking;

Figure 4 is a diagrammatic cross-sectional view of the device of Figure 3 after polymerisation or crosslinking to provide an STN LCD constituting a first embodiment of the invention;

Figure 5 is a graph of transmittance against applied voltage for the devices shown in Figure 3 and 4 with cross polarisers;

Figure 6 is a graph of transmittance in arbitrary units against applied voltage for a device of the type shown in Figure 4 with parallel polarisers;

Figure 7 is a diagrammatic cross-sectional view of an STN LCD of the reflective type constituting a second embodiment of the invention; and

Figure 8 is a diagrammatic cross-sectional view of an STN LCD constituting a third embodiment of the invention.

[0038] Like reference numerals refer to like parts throughout the drawings.

[0039] The device shown in Figure 3 comprises a liquid crystal cell disposed between external polarisers 10 and 11. The polarisers 10 and 11 are linear polarisers and their polarisation directions may be between 0° and 90° with respect to each other.

[0040] The liquid crystal cell comprises an upper substrate 12 and a lower substrate 13. The substrates 12 and 13 carry addressing arrangements shown as electrodes 14 and 15. For instance, in the case of passive matrix addressing, the electrodes 14 and 15, which are transparent and may be made of indium tin oxide (ITO), comprise parallel strips oriented such that the longitudinal direction of the electrodes 14 is orthogonal to the longitudinal direction of the electrodes 15. The intersections or overlaps of the electrodes 14 and 15 define picture elements (pixels) which are independently addressable.

[0041] Alternatively, an active matrix addressing arrangement may be provided. In such an arrangement, one of the electrodes such as 15 is a plan electrode, ie: extends substantially continuously throughout the device. The other electrode, such as 14, is divided into individual pixel electrodes, each of which is controlled by one or more active devices provided on the substrate 12, for instance, in the form of thin film transistors made by silicon-on-glass-techniques.

[0042] The electrodes 14 and 15 are covered by alignment layers 16 and 17, respectively. Two alignment layers are shown in the embodiment illustrated in Figure 3 but, in alternative arrangements, it is possible to omit one of the alignment layers. The alignment layers 16 and 17 are, for instance, made of rubbed polyimide, such as P12555 available from Dupont, with the rubbing directions being orthogonal and such as to provide a left-handed liquid crystal twist. The alignment layers provide a relatively low pre-tilt angle, for instance of 2 degrees.

[0043] During manufacture, the liquid crystal cell is filled with a mixture 18 comprising a liquid crystal and a prepolymer. For example, the liquid crystal may be of a nematic type and may comprise ZLI2293 available from Merck in Germany. The prepolymer may comprise a chiral diacrylate and a non-chiral diacrylate. The chiral diacrylate comprises 0.42% by weight of the mixture and may be LC481 which is available from BASF in Germany and which has a helical twisting power substantially equal to 34.5 per micrometre. The non-chiral diacrylate may comprise 1.5% by weight of the mixture and may be RM258 available from Merck in the UK.

[0044] The device comprises a supertwisted nematic device with the liquid crystal in the mixture 18 exhibiting a twist substantially equal to 270° , the helical pitch being substantially equal to 6.7 micrometres.

[0045] The diacrylates in the mixture 18 are photopolymerisable and, after filling of the cell, are exposed to Type A ultraviolet radiation with an intensity of 14 milliwatts per square centimetre applied for 30 seconds. As a result, the diacrylates are crosslinked to form a polymer network so that the cell contains a mixture of the liquid crystal and the polymer network as shown at 19 in Figure 4.

[0046] Figure 5 illustrates the performance of the device before photopolymerisation as illustrated in Figure 3 and after photopolymerisation as illustrated in Figure 4. In particular, the electrooptic curve for the device before photopolymerisation is shown at 20 whereas that for the device after photopolymerisation is shown at 21. The device is of the type having polarisers 10 and 11 aligned with the polarising directions orthogonal so as to provide a normally-white or normally-bright device. The electrooptic curve 21 is substantially steeper than the curve 20 and this is substantially due to the reduction or suppression of the formation of the striped texture during switching.

[0047] As a result of locking the chirality of the polymer network, the possibility of formation of the striped texture is prevented or substantially reduced. Thus, it is possible to produce a 270° STN device with an alignment layer inducing a pre-tilt of 2° which can be commercially manufactured. Such a device is advantageous as compared with conventional STN devices where the twist is limited to 240° with alignment layers inducing a relatively high pre-tilt, for instance greater than 4° . Moreover, it is possible to avoid the use of commercially unviable evaporated alignment layers, such as silicone oxide, which would otherwise be required in order to provide high pre-tilt alignment layers permitting a 270° twist.

[0048] Figure 6 is an electrooptic curve for a device of the type shown in Figure 4 but with the polarisation directions of the polarisers 10 and 11 parallel to each other to provide a normally-black or a normally-dark display. The curves 21 and 22 are obtained for switching in both directions between dark and bright states and illustrate that devices of the type shown in Figure 4 are substantially free from hysteresis.

[0049] The use of a networked polymer as compared to a side chain polymer provides more stable polymer orientation and avoids hysteresis in the electrooptic curve. Additionally, the use of low pre-tilt alignment layers reduces device switching times so that the required time to switch between two states of a typical device may be of the order of 40 milliseconds.

[0050] The device shown in Figure 4 is of the transmissive type whereas Figure 7 illustrates a device of the reflective type. In this case, the polariser 11 is omitted and the electrode 15 is replaced by a combined elec-

trode and mirror 25. Otherwise, the device may be of the same type as illustrated in Figure 4 and may be made in the same way.

[0051] The liquid crystals of the mixtures 19 shown in Figures 4 and 7 are of the positive dielectric anisotropy type and the photopolymerisation of the chiral and non-chiral prepolymers having at least two polymerisable groups (diacrylates in the examples specifically described hereinbefore) occurs with no applied field across the liquid crystal cell. However, it is also possible to use nematic liquid crystal of negative dielectric anisotropy. In this case, as shown in Figure 8, a signal generator 16 applies a sufficiently high electric field across the mixture in the cell during photopolymerisation so that the liquid crystal is substantially planar during the polymerisation. This results in a mixture 27 which, when the field is removed, comprises a planar polymer network with a homeotropic liquid crystal.

Claims

1. A supertwisted nematic liquid crystal device comprising first and second substrates defining therebetween a cell containing a mixture of a nematic liquid crystal and a helical polymer network, characterised in that the polymer of the network comprises at least one polymerised chiral prepolymer.
2. A device as claimed in claim 1, characterised in that the nematic liquid crystal in the cell has a twist angle of between substantially 180° and substantially 360° .
3. A device as claimed in claim 2, characterised in that the twist angle is greater than 240° .
4. A device as claimed in claim 2, characterised in that the twist angle is substantially equal to 270° .
5. A device as claimed in any one of the preceding claims, characterised in that the nematic liquid crystal in the cell has a pre-tilt angle less than 4° .
6. A device as claimed in claim 5, characterised in that the pre-tilt angle is substantially equal to 2° .
7. A device as claimed in any one of the preceding claims, characterised in that at least one of the first and second substrates has an alignment layer for inducing planar alignment.
8. A device as claimed in any one of the preceding claims, characterised in that the polymer of the network is a networked polymer.
9. A device as claimed in any preceding claim, characterised in that the chiral prepolymer comprises at

- least two polymerisable or crosslinkable groups.
10. A device as claimed in any preceding claim, characterised in that the prepolymer comprises a diacrylate.
 11. A device as claimed in any one of the preceding claims, characterised in that the polymer network comprises at least one per cent by weight of the mixture.
 12. A device as claimed in claim 11, characterised in that the polymer comprises at least 1.5 per cent by weight of the mixture.
 13. A device as claimed in any one of the preceding claims, characterised in that the polymer network comprises less than 20 per cent by weight of the mixture.
 14. A device as claimed in claim 13, characterised in that the polymer network comprises less than ten per cent by weight of the mixture.
 15. A device as claimed in claim 14, characterised in that the polymer network comprises less than five per cent by weight of the mixture.
 16. A device as claimed in any one of the preceding claims, characterised in that the cell is disposed between first and second polarisers.
 17. A device as claimed in claim 16, characterised in that the first and second polarisers have linear polarising directions, oriented at between 0° and 90° with respect to each other.
 18. A device as claimed in any one of claims 1 to 15, characterised in that the cell is disposed between a polariser and a reflector.
 19. A method of making a supertwisted nematic liquid crystal device, comprising juxtaposing first and second substrates to define therebetween a cell, filling the cell with a mixture comprising a nematic liquid crystal and a prepolymer, and polymerising or crosslinking the prepolymer to form a polymer network, characterised in that the prepolymer is a chiral prepolymer.
 20. A method as claimed in claim 19, characterised in that the mixture comprises a non-chiral prepolymer in addition to the chiral prepolymer.
 21. A method as claimed in claim 19 or 20, characterised in that the prepolymer is a networkable prepolymer.
 22. A method as claimed in any one of claims 19 to 21, characterised in that the chiral prepolymer has at least two polymerisable or crosslinkable groups.
 23. A method as claimed in claims 22, characterised in that the prepolymer comprises a diacrylic.
 24. A method as claimed in any one of claims 19 to 23, characterised in that the nematic liquid crystal in the cell has a twist angle of between substantially 180° and substantially 360°.
 25. A method as claimed in claim 24, characterised in that the twist angle is greater than 240°.
 26. A method as claimed in claim 25, characterised in that the twist angle is substantially equal to 270°.
 27. A method as claimed in any one of claims 19 to 26, characterised in that the nematic liquid crystal in the cell has a pre-tilt angle less than 4°.
 28. A method as claimed in claim 27, characterised in that the pre-tilt angle is substantially equal to 2°.
 29. A method as claimed in any one of claims 19 to 28, characterised by forming on at least one of the first and second substrates, prior to the juxtaposition, an alignment layer for inducing planar alignment.
 30. A method as claimed in any one of claims 19 to 29, characterised in that the prepolymer comprises at least one per cent by weight of the mixture.
 31. A method as claimed in claim 30, characterised in that the prepolymer comprises at least 1.5 per cent by weight of the mixture.
 32. A method as claimed in any one of claims 19 to 31, characterised in that the prepolymer comprises less than 20 per cent by weight of the mixture.
 33. A method as claimed in claim 32, characterised in that the prepolymer comprises less than ten per cent by weight of the mixture.
 34. A method as claimed in claim 33, characterised in that the prepolymer comprises less than five per cent by weight of the mixture.
 35. A method as claimed in any one of claims 19 to 34, characterised in that the liquid crystal has positive dielectric anisotropy and the polymerising or crosslinking is performed in the absence of an applied field across the cell.
 36. A method as claimed in any one of claims 19 to 34, characterised in that the liquid crystal has negative

dielectric anisotropy and, during the polymerising or crosslinking, a field which provides planar alignment of the liquid crystal is applied across the cell.

5

10

15

20

25

30

35



40



45



50



55

7











European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 98 30 7529

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
X,P	MITOV M ET AL: "MORPHOLOGICAL STUDY OF A CHIRAL POLYMER NETWORK IN A NEMATIC LIQUIDCRYSTAL FROM A CONCENTRATION GRADIENT" LIQUID CRYSTALS, vol. 23, no. 6, December 1997, pages 903-910, XP000726024 * the whole document *	1	C09K19/54 C09K19/02
Y	EP 0 359 146 A (DAINIPPON INK AND CHEMICALS) 21 March 1990 * page 5, line 42 - page 6, line 18; example 1 *	1,9,10, 19,29	
Y	EP 0 313 053 A (DAINIPPON INK AND CHEMICALS) 26 April 1989 * page 2, line 52 - page 3, line 8 * * page 3, line 41 - line 44 * * page 13, line 55 - page 14, line 35 *	1,9,10, 19,29	
Y	WO 92 19695 A (KENT STATE UNIVERSITY) 12 November 1992 * page 4, line 14 - line 32 * * page 9, line 12 - line 31 *	1,9-15, 19,29	TECHNICAL FIELDS SEARCHED (Int.Cl.6) C09K
Y,P	US 5 674 576 A (T.GOTOH) 7 October 1997 * column 2, line 36 - column 3, line 15 * * column 6, line 10 - line 18 * * column 7, line 7 - column 8, line 20 * * column 8, line 26 - column 9, line 62; examples 1-4 *	1,9-15, 19,29	
-/--			
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 18 December 1998	Examiner Boulon, A
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03/82 (P04C01)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 98 30 7529

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
A	<p>DATABASE INSPEC INSTITUTE OF ELECTRICAL ENGINEERS, STEVENAGE, GB Inspec No. 5744537, TAKATSU H ET AL: "UV curable liquid crystals and their application" XP002088518 * abstract *</p> <p>& LIQUID CRYSTALS FOR ADVANCED TECHNOLOGIES. SYMPOSIUM, LIQUID CRYSTALS FOR ADVANCED TECHNOLOGIES. SYMPOSIUM, SAN FRANCISCO, CA, USA, 8-11 APRIL 1996, pages 293-303, 1996, Pittsburgh, PA, USA, Mater. Res. Soc, USA</p> <p>-----</p>	1	
			TECHNICAL FIELDS SEARCHED (Int.Cl.6)
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 18 December 1998	Examiner Boulon, A
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background D : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons</p> <p>& : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03 82 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 98 30 7529

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

18-12-1998

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 359146	A	21-03-1990	JP 2202982 A	13-08-1990
			JP 2202987 A	13-08-1990
			JP 2272423 A	07-11-1990
			JP 2073883 A	13-03-1990
			JP 2733986 B	30-03-1998
			JP 2075688 A	15-03-1990
			JP 2733992 B	30-03-1998
			JP 2075691 A	15-03-1990
			JP 2075692 A	15-03-1990
			JP 2733995 B	30-03-1998
			JP 2075693 A	15-03-1990
			JP 2733996 B	30-03-1998
			JP 2086693 A	27-03-1990
			JP 2734000 B	30-03-1998
			DE 68917233 D	08-09-1994
			DE 68917233 T	09-02-1995
			US 5374371 A	20-12-1994
EP 313053	A	26-04-1989	JP 1252689 A	09-10-1989
			JP 2711546 B	10-02-1998
			JP 1198725 A	10-08-1989
			JP 2724596 B	09-03-1998
			JP 2085822 A	27-03-1990
			JP 2811683 B	15-10-1998
			CA 1307576 A	15-09-1992
			DE 3854910 D	29-02-1996
			DE 3854910 T	04-07-1996
			US 5304323 A	19-04-1998
WO 9219695	A	12-11-1992	CA 2102199 A	03-11-1992
			CN 1070744 A	07-04-1993
			EP 0582656 A	16-02-1994
			IL 101766 A	12-09-1996
			JP 6507505 T	25-08-1994
			NO 933845 A	23-12-1993
			US 5453863 A	26-09-1995
			US 5691795 A	25-11-1997
			US 5695682 A	09-12-1997
			US 5384067 A	24-01-1995
			US 5437811 A	01-08-1995
US 5674576	A	07-10-1997	JP 2531468 B	04-09-1996
			JP 8092561 A	09-04-1996
			JP 2723060 B	09-03-1998
			JP 8166603 A	25-06-1996
			JP 2710222 B	10-02-1998

EPO FORM P449

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

THIS PAGE BLANK (USPTO)